

Designation	EN	UNS	AISI	LMSA
<b>X5CrNi18-10</b>	1.4301	S30400	304	D110

## Chemical composition (Weight %)

Fe	C	Cr	Ni	Si	Mn	P	S	N
Balance	< 0.07	17.0-19.5	8.0-10.5	≤ 1.0	≤ 2.0	≤ 0.045	≤ 0.015	≤ 0.110

In order to achieve maximum homogeneity and consistent quality, the actual tolerances on both alloy components and impurities are significantly tighter and more precisely defined than the standard composition indicated.

## Main technical properties and features

Austenitic stainless steels are amongst the most popular and most widely used of the stainless steel family. They have a chromium content of around 17% and comprise nickel and possibly other additives such as molybdenum, titanium or niobium. It is the nickel content which enables the austenitic structure that supports corrosion resistance. In fact, the absence of a second phase, such as strain induced martensite or ferrite promotes the corrosion resistance. Austenitic stainless steel 1.4301, X5CrNi18-8, is very widely used because of its excellent intercrystalline corrosion resistance, very good cold deformability, good deep drawing capability and its good aptitude for welding. The 1.4301, X5CrNi18-8, preserves its excellent corrosion resistance up to 300°C but can also be used at very low temperatures for cryogenic applications. In the soft temper, alloy 1.4301, X5CrNi18-8, is practically non-magnetic. The work hardening effect during cold deformation is rather weak. For example, it does not reach the spring properties of stainless steel 1.4310, X10CrNi18-8. Lamineries MATTHEY can produce the 1.4301, X5CrNi18-8, in various tempers ranging from dead soft to extra hard rolled.

## Typical manufacturing range

		Thickness (mm)	Width (mm)	Length (mm)
<b>Rolled products</b>	Strip in coils <sup>1)</sup>	0.010 - 2.000	1.5 - 200.0	-
	Strip as sheets <sup>1)</sup>	0.015 - 1.500	10.0 - 200.0	100 - 3000

1) Not all our production possibilities are presented here. Other dimensions or other product forms available upon request. Certain combinations of thicknesses and widths are not possible.

## Mechanical properties of strips

Temper		Tensile strength, Rm (N/mm <sup>2</sup> )	Hardness HV
C500 <sup>1), 2)</sup>	soft	500-700	150-200
C700 <sup>1), 2)</sup>	soft	650-850	190-250
C850 <sup>1)</sup>	¼ hard	680-1000	200-300
C1000 <sup>1)</sup>	½ hard	950-1150	250-390
C1150 <sup>1)</sup>	hard	1100-1300	310-420
C1300 <sup>1)</sup>	extra hard	1250-1550	380-500

1) These tempers do not correspond exactly to the EN 10151 and EN 10088 standards and are only indicative.

2) Temper C500, soft is only available for thicknesses higher or equal to 0.1 mm. For thicknesses < 0.1mm, soft corresponds to the C700 temper.

The information in this document is informative only. Information provided does not constitute any contractual commitment or warranty of any kind.



---

<b>Designation</b>	<b>X5CrNi18-10</b>	EN 1.4301	UNS S30400	ASI 304	LMSA D110
--------------------	--------------------	--------------	---------------	------------	--------------

---

## Physical properties

Modulus of elasticity	kN/mm <sup>2</sup>	200 (180 à 300°C, 165 à 500°C))
Poisson ratio		0.3
Density	kg/dm <sup>3</sup>	7.9
Melting point / Melting range	°C	1420-1470
Linear dilatation coefficient (20-300°C)	10 <sup>-6</sup> / °C	16 (17 à 300°C, 18 à 500°)
Thermal conductivity at 20°C	W/m °K	15
Electrical resistivity	μΩcm	0.73
Electrical conductivity	MS/m	1.4
Specific heat at 20°C	J/(kg K)	500
Magnetic properties		Can be slightly magnetic in soft temper. Its magnetism increases with work hardening (also with its hardness and its tensile strength).

## Typical uses

Thanks to its corrosion resistance, the 1.4301 is widely used in the chemical industry, cutlery, watches and clocks, medical devices, appliances etc. The 1.4301, X5CrNi18-10, as delivered by Lamineries MATTHEY SA is frequently used to manufacture parts such as spring components, pressure membranes, various watch components, deep drawn parts, connectors etc



<b>Designation</b>	<b>X5CrNi18-10</b>	EN 1.4301	UNS S30400	ANSI 304	LMSA D110
--------------------	--------------------	--------------	---------------	-------------	--------------

### Tolerances

Thickness	Thickness (mm)		Lamineries MATTHEY SA		
	≥	<	LMSA Standard	LMSA Precision	LMSA Extreme
<p>The table shown is an outline of our typical thickness tolerances available. They are tighter than industry standards.</p> <p>Our "Precision" and "Extreme" tolerances are available upon request.</p>		0.025	-	-	± 0.001
	0.025	0.050	± 0.003	± 0.002	± 0.0015
	0.050	0.065	± 0.004	± 0.003	± 0.002
	0.065	0.100	± 0.006	± 0.004	± 0.003
	0.100	0.125	± 0.008	± 0.006	± 0.003
	0.125	0.150	± 0.008	± 0.006	± 0.004
	0.150	0.250	± 0.010	± 0.008	± 0.004
	0.250	0.300	± 0.012	± 0.008	± 0.005
	0.300	0.400	± 0.012	± 0.009	± 0.005
	0.400	0.500	± 0.015	± 0.010	± 0.006
	0.500	0.600	± 0.020	± 0.012	± 0.007
	0.600	0.800	± 0.020	± 0.014	± 0.007
	0.800	1.000	± 0.025	± 0.015	± 0.009
	1.000	1.200	± 0.025	± 0.018	± 0.0012
	1.200	1.250	± 0.030	± 0.020	± 0.0012
1.250	1.500	± 0.035	± 0.025	± 0.0014	

### Width

Our width tolerance is + 0.2 -0.0 mm (or ± 0.1 mm upon request). They are available for slit widths < 125 mm and thicknesses < 1.00 mm. Special tolerances upon request.

Camber	Width (mm)		Camber max. (mm/m)			
	>	≤	LMSA standard		LMSA extreme	
			≤ 0.5 mm	> 0.5 mm	≤ 0.5 mm	> 0.5 mm
<p>Our tolerance "standard" respects the EN Standard 1654 (Length of measurement 1000 mm). Other tolerances upon request.</p>	3	6	12	-	6	-
	6	10	8	10	4	5
	10	20	4	6	2	3
	20	250	2	3	1	1.5

### Surface

Special surface qualities upon request

### Flatness

Special requirement on the longitudinal or transversal flatness upon request