

Designation	Duratherm 600 (CoNiCr)	UNS	AISI	LMSA
		-	2.4781	F135

Chemical composition

Ni	Co	Cr	Fe	W	Mo	Ti	Al	Mn	Si
Bal.	40.0 - 43.0	10.5 - 13.5	8.0 - 10.0	3.0 - 5.0	3.0 - 5.0	1.0 - 3.0	0.50 - 1.5	0.5 - 1.5	0.3 - 1.0

Values (Weight %). In order to achieve maximum homogeneity and consistent quality, the actual manufacturing tolerances are tighter and more precisely than the composition indicated.

Main technical properties and features

Duratherm® 600 is a superalloy developed by VACCUMSCHMELZE and belonging to the group of age-hardenable cobalt-nickel-chromium multi-phase materials. This alloy has excellent corrosion resistance, especially in environments containing hydrogen sulfide (H₂S).

Duratherm® is a material of choice for spring applications, it has excellent ductility and formability in the soft temper, and the spring properties can be enhanced with cold-working. This alloy can be hardened by precipitation in the soft temper, and the spring properties reach their maximum after the precipitation hardening treatment. Hardening treatment takes place at a temperature between 650°C and 750°C, for 2 - 4 hours.

Lamineries MATTHEY offers cold rolled products in the form of strips and plates made of Duratherm® 600 alloy.

Typical uses

Various types of springs, automotive industry, military industry, watch industry, measuring instruments, loudspeakers, membranes for pressure gauges, retention springs in the chemical industry, electronic and micro technical industry, etc.

Typical manufacturing range

	Thickness (mm)	Width (mm)	Length (mm)
Rolled products Strip in coils ^[1]	0.010 - 1.000	1.5 - 200.0	-
Strip as sheets ^[1]	0.015 - 1.000	10.0 - 200.0	100 - 3000

^[1] Not all our production possibilities are presented here. Other dimensions or product forms available upon request. Some combinations of thicknesses and widths are not possible.

Mechanical properties of strips

Temper	R _m (N/mm ²)	R _{p0.2} (N/mm ²)	A _{50mm} (%)	Hardness HV
R800 soft	800 - 920	250 - 450	35	190 - 230
R900 soft + skin pass	800 - 950	300 - 470	30	200 - 250
R950 ½ hard	950 - 1200	700 - 1100	5	300 - 400
R1300 hard	1300 - 1550	1100 - 1450	-	400 - 520
R1550 spring	1550 min.	1400 min.	-	510 min.

Physical properties

Modulus of elasticity	kN/mm ²	205 (untreated) / 225 (treated)
Density	g/cm ³	8.45 (untreated) / 8.50 (treated)
Melting point	°C	1350
Linear dilatation coefficient (20 to 100°C)	10 ⁻⁶ /°C	13.50 (untreated) / 13.50 (treated)
Thermal conductivity at 20°C	W/m °K	10.00 (untreated) / 10.00 (treated)
Electrical conductivity	MS/m	0.95 (untreated) / 1.05 (treated)
Permeability (H = 300A/cm)		1.02 (untreated) / 1.015 (treated)

Tolerances (strip and foil)

Thickness	Thickness (mm)		Lamineries MATTHEY			
	≥	<	LMSA Standard	LMSA Precision	LMSA Extreme	
	-	0.025	-	-	± 0.001	
	0.025	0.050	± 0.003	± 0.002	± 0.0015	
	0.050	0.065	± 0.004	± 0.003	± 0.002	
	0.065	0.100	± 0.006	± 0.004	± 0.003	
	0.100	0.125	± 0.008	± 0.006	± 0.003	
	0.125	0.150	± 0.008	± 0.006	± 0.004	
	0.150	0.250	± 0.010	± 0.008	± 0.004	
	0.250	0.300	± 0.012	± 0.008	± 0.005	
	0.300	0.400	± 0.012	± 0.009	± 0.005	
	0.400	0.500	± 0.015	± 0.010	± 0.006	
	0.500	0.600	± 0.020	± 0.012	± 0.007	
	0.600	0.800	± 0.020	± 0.014	± 0.007	
	0.800	1.000	± 0.025	± 0.015	± 0.009	
	1.000	1.200	± 0.025	± 0.018	± 0.012	
	1.200	1.250	± 0.030	± 0.020	± 0.012	
	1.250	1.500	± 0.035	± 0.025	± 0.014	
Width	Our width tolerances "Standard" is +0.2, -0.0 (or ± 0.1 mm upon request). They are available for slit widths < 125 mm and thicknesses < 1.00 mm. Special tolerances upon request.					
Camber	Width (mm)		Camber max. (mm/m)			
	>	≤	LMSA standard		LMSA extreme	
			≤ 0.5 mm	> 0.5 mm	≤ 0.5 mm	> 0.5 mm
	3	6	12	-	6	-
	6	10	8	10	4	5
	10	20	4	6	2	3
	20	250	2	3	1	1.5
Surface	Special surface qualities upon request					
Flatness	Special requirement on the longitudinal or transversal flatness upon request					

The information in this document is informative only. Information provided does not constitute any contractual commitment or warranty of any kind.